

TEST REPORT



Report number

21.00216.2

Date of test

21 April 2021

Date report

29 April 2021

Applicant

**Soudal N.V.
Everdongenlaan 18
2300 Turnhout
Belgium**

bezoekadres
Poppenbouwing 56
4191 NZ Geldermalsen

postadres
Postbus 202
4190 CE Geldermalsen

T +31 (0)88 244 01 00
F +31 (0)88 244 01 01
E info@skgikob.nl
I www.skgikob.nl

Size report

This report consists of 18 pages (including appendices)

Subject

Determination of the

- Air permeability according EN 12114 (conform § 4.2.2. BRL 2804-1)
- Flow coefficient C according EN 12114

of a seal type: Soudatight SP

Inspector

R. Jonkergouw

Technical manager

dr. ir. A. van Beek

Conclusion

The seal Soudatight SP meets the classification as hereby mentioned:

- Air permeability according EN 12114
 - at positive pressure **1.000 Pa** **< 0.1** **m³/hm¹**
 - at negative pressure **-1.000 Pa** **< 0.1** **m³/hm¹**
- Flow coefficient C **NPD** **dm³/(s.Paⁿ)**

- Air permeability additional tested
 - at positive pressure **1.750 Pa** **0,27** **m³/hm¹**